



Stannous Octoate

Packing: 25 kg cans

Guarantee period of storage - 12 months

Quality data in accordance with TU 6-02-539-75:

Appearance at 25-30°C	Viscous homogeneous liquid without precipitate and foreign admixtures
Color or chromaticity according to iodometric scale, mg I ₂ /100 sm ³ , not more than	30
Divalent Tin, Sn, %	not less than 27
Total Tin, Sn, %	28-31
Viscosity, cPs	270-490
Density at 20 °C, g/cm ³	1,23-1,28

Application:

- linking agent in obtaining of foamed polyurethanes;
- catalyst of cold vulcanization of polysiloxane rubber resins